

Technical Data

Distributed By: KPR Adcor Inc USA & Canada TOLL FREE 1-866-577-2326 Phone: 905-628-2529 Fax 905-628-2529 E-mail: kpr@corrosionvci.com

UNIWRAP[®] MPI UW30MPI Preliminary

PRODUCT DESCRIPTION

A 30 lb./ream (49 g/m²) natural kraft saturated with Daubert Cromwell multi-metal Uniwrap[®] MPI volatile corrosion inhibitor (VCI) formulation. Designed for protecting ferrous/non-ferrous metals combinations including cadmium and zinc galvanized steel. (*Note: Previous names UW30A, Ferro-Pak 30MPI*).

PHYSICAL PROPERTIES

Coating Deposition: 6.5 lb./ream (11g/m²) minimum

				<u>Test</u>
Property	<u>Units</u>	Typical Value		Method
Basis Weight	lb./ream (g/m ²)	38 (62)		T-410
Caliper	mil (µm)	3.7 (94)		T-411
Mullen Burst	psi (kPa)	21 (144)		T-403
				Test
		MD	CD	Method
Elmendorf Tear	g/ply (mN/ply)	51 (500)	57 (559)	T-414
Tensile Strength	lb./in. (kN/m)	19 (3.2)	11 (1.9)	T-404

INHIBITOR PROTECTION

Classified as six months protection when stored outside and properly protected from moisture and other environmental elements; 24 months minimum, inside dry storage.

<u>Metal</u>	Corrosion Protection
Mild carbon steel and cast iron	Provides full protection in contact and vapor phases
Aluminum	Passive; Test for compatibility
Zinc and zinc galvanized steel	Provides full protection in contact and vapor phases

UNIWRAP® MPI UW30MPI

<u>Metal</u>	Corrosion Protection
Copper	Provides full protection in contact and vapor phases
Brass ¹	Provides full protection in contact and vapor phases
Bronze	Provides full protection in contact and vapor phases
Silver	May protect; Test for compatibility
Category A ²	Provides full protection in contact and vapor phases
Category B ³	May protect; Test for compatibility

- 1 Brass alloys in the "red" area containing up to 20% zinc will act like copper; brass in the "white" area containing over 20% zinc and will act like Category A metals.
- Category A metals include zinc, cadmium, nickel, cadmium-plated steel, and nickel-plated steel. 2 These are prone to contact corrosion sensitivity with inhibitor chemicals, but will be protected as shown in the vapor phase.
- Category B metals include lead, antimony, babbitt alloys, solder, magnesium or magnesium alloys. 3

The data, statements and recommendations in this product information sheet are based on testing, research and other development work, which has been carefully conducted by us, and we believe such data. Liability under this warranty is limited to the net statements and recommendations will serve as reliable guidelines. Physical properties shown above represent typical values and are not intended for use in writing specifications. However, this product is subject to numerous uses under varving conditions over which we have no control, and accordingly, we do NOT warrant that this product is suitable for any particular use. Users are advised to test the product in advance to make certain it is suitable for their particular production conditions and use.

WARRANTY - All products manufactured by us are warranted to be first class material and free from defects in material and workmanship. purchase price of any such products proven defective or, at our option, to the repair or replacement of said products upon their return to us transportation prepaid. All claims on defective products must be made in writing within 30 days after the receipt of such products in your plant and prior to further processing or combining with other material and products.

WE MAKE NO WARRANTY, EXPRESS OR IMPLIED, AS TO THE SUITABILITY OF ANY OF OUR PRODUCTS FOF ANY PARTICULAR USE, AND WE SHALL NOT BE SUBJECT TO LIABILITY FROM ANY DAMAGES RESULTING FROM THEIR USE IN OPERATIONS NOT UNDER OUR DIRECT CONTROL.

THIS WARRANTY IS EXCLUSIVE OF ALL OTHER WARRANTIES, EXPRESS OR IMPLIED, AND NO REPRESENTATIVE OF OURS OR ANY OTHER PERSON IS AUTHORIZED TO ASSUME FOR US ANY OTHER LIABILITY IN CONNECTION WITH THE SALE OF OUR PRODUCTS.

SMD: 03/13/02 Revised: 3/22/05 JB