

Kpr Adcor Inc.  
USA & Canada

Toll free: (866) 577-2326  
Tel: 905-628-3232  
Fax: 905-628-2529

Web site: [www.corrosionvci.com](http://www.corrosionvci.com)  
Email: [kpr@corrosionvci.com](mailto:kpr@corrosionvci.com)

**DAUBERT VCI® NOX-RUST® LIQUID  
9900**  
(Water based barrier coating  
Soft, firm, very clear, removable film)

Daubert VCI Nox-Rust 9900 is a carefully selected blend of inhibitors, emulsifiers, and surfactants, designed to deposit a barrier coat from a water emulsion system. Nox-Rust 9900 is intended for use in applying a final preservative coating to production parts prior to storage or shipment.

**Application and Removal**

Nox-Rust 9900 can be applied by dipping, spraying or flow coating. Industrial alkaline cleaners at a temperature of 170-200°F or petroleum solvents such as mineral spirits can be used for removal of the product.

**Uses**

Suggested uses for Nox-Rust 9900 are engine blocks, valves, gears, tool and dies, bushings, taps, chains and numerous other metal products where a non-flammable product which deposits a hard barrier type film is desired.

**Physical Characteristics**

(Typical Values, Not Specifications)

Appearance	Amber-colored, clear, aqueous solution
pH	8.0-9.0
Specific Gravity @72°C	1.01
Lbs./Gal.	8.3
Flash point (°F)	Non-flammable
Solids by weight %	32.3
Solids by volume %	31.1
Film type	Hard, clear, very thin

**Test results**

(Typical Values, Not Specifications)

5% salt spray (ASTM-B-117-64)	150 Hours (minimum)
Humidity cabinet (ASTM-D-1748)	200 Hours (minimum)

**Suggested duration of use**

Outdoor Storage- Uncovered	1-3 months
Covered	1-2 years
Indoor Storage- Uncovered	2-3 years
Covered or packaged	3-5 years

The data, statements and recommendations in this product information sheet are based on testing, research and other development work, which has been carefully conducted by us, and we believe such data, statements and recommendations will serve as reliable guidelines. Physical properties shown above represent typical values and are not intended for use in writing specifications. However, this product is subject to numerous uses under varying conditions over which we have no control, and accordingly, we do NOT warrant that this product is suitable for any particular use. Users are advised to test the product in advance to make certain it is suitable for their particular production conditions and use.

**WARRANTY** – All products manufactured by us are warranted to be first class material and free from defects in material and workmanship. Liability under this warranty is limited to the net purchase price of any such products proven defective or, at our option, to the repair or replacement of said products upon their return to us transportation prepaid. All claims on defective products must be made in writing within 30 days after the receipt of such products in your plant and prior to further processing or combining with other material and products.

WE MAKE NO WARRANTY, EXPRESS OR IMPLIED, AS TO THE SUITABILITY OF ANY OF OUR PRODUCTS FOR ANY PARTICULAR USE, AND WE SHALL NOT BE SUBJECT TO LIABILITY FROM ANY DAMAGES RESULTING FROM THEIR USE IN OPERATIONS NOT UNDER OUR DIRECT CONTROL.

THIS WARRANTY IS EXCLUSIVE OF ALL OTHER WARRANTIES, EXPRESS OR IMPLIED, AND NO REPRESENTATIVE OF OURS OR ANY OTHER PERSON IS AUTHORIZED TO ASSUME FOR US ANY OTHER LIABILITY IN CONNECTION WITH THE SALE OF OUR PRODUCTS.